TATA STEEL



Ymagine® D1

Optimised for drawing - formable, clean and consistent

Ymagine is Tata Steel's range of high-quality, direct-rolled steel products engineered for reliable performance and efficient processing. Supplied pickled and oiled, Ymagine offers excellent dimensional control, consistent mechanical properties and tight tolerances – making it a smart alternative to cold-rolled or hot-rolled steel. All grades are delivered in weld-free coils and available in various

thicknesses, widths and coil weights to optimise productivity and reduce waste.

Ymagine D1 is a low-carbon, direct-rolled steel designed for excellent deep-drawing and cold-forming performance. Ideal for pressed parts, household appliances and interior automotive panels, it provides smooth processing and reliable dimensional results.

Mechanical properties (measured transverse to the rolling direction)

		MinMax. tensile strength	% elongation at fractur	e
	MinMax. yield strength		t < 3 mm	t ≥ 3 mm
	R _p in MPa	R _m in MPa	L ₀ =80 mm (%)	$L_0 = 5.65 \sqrt{S_0} \text{ mm (%)}$
Typical	290	380	28	34
Guaranteed	210-360	335-425	≥ 23	≥ 28

Chemical composition (% by weight)

	C	Mn	P	S	Si ¹
Typical	0.045	0.220	0.008	0.007	0.018
Guaranteed	≤ 0.065	≤ 0.300	≤ 0.025	≤ 0.015	≤ 0.035

For the purpose of batch galvanising, Ymagine® D1 can be ordered after consultation with a maximum Si content of 0.030%.

Tolerances

Thickness	Tolerances	
$1.15 \le t \le 2.0$	± 0.05	
2.0 < t ≤ 2.5	± 0.06	
2.5 < t ≤ 3.0	± 0.07	
$3.0 < t \le 4.0$	± 0.09	
	\pm 0.07 on request	

Weldability

Ymagine can be welded using all conventional welding processes. Thanks to the low content of residual elements, the material offers good weldability, comparable to that of hot-rolled or cold-rolled steel with a similar chemical composition.

Surface quality

The surface quality of Ymagine is more than sufficient for hot-rolled and cold-rolled applications that are not surface critical. The surface roughness is comparable to that of hot-rolled pickled and oiled material, i.e. 1-3 μ m Ra (cut-off length = 2.5 mm).

Coatability

Ymagine has been tested for both wet paint and powder coatings. Adhesion test results were positive on flat sample material, indicating good coatability.


Galvanising

Ymagine can be hot-dip galvanised without any restrictions.

Product support

Our proactive Customer Technical Services team is available to help you optimise your processes and maximise performance with tailored advice and hands-on support. Backed by deep steel expertise and in-depth application knowledge, we'll work with you to boost efficiency, reduce waste, and get the best out of Ymagine D1.

Available dimensions of Ymagine® D1



Ymagine® range

Steel grades: Ymagine D1 - drawing steel

Ymagine S1 – structural steel High-strength low-allow steels: H240, H320, H360, H420, H500

Thickness range: 1.15 – 4 mm

Width range: 1000 – 1530 mm

Surface treatment: pickled and oiled

Further information

E: connect.engineering@tatasteeleurope.com

Tata Steel Nederland

Engineering Wenckebachstraat 1 1951 JZ Velsen-Noord The Netherlands

E: connect.engineering@tatasteeleurope.com www.tatasteelnederland.com/products

E0155:EN:PDF:0925

www.tatasteelnederland.com

Ymagine® is a registered trademark of Tata Steel Nederland.

While care has been taken to ensure that the information contained in this publication is accurate, neither Tata Steel, nor its subsidiaries, accept responsibility or liability for errors or for information which is found to be misleading.

Before using products or services supplied or manufactured by Tata Steel and its subsidiaries, customers should satisfy themselves as to their suitability.

Copyright 2025 Tata Steel IJmuiden B.V.



Scan for the latest product information