



Colorcoat® SDP 50 Colours



Printed colours are for guidance only.

Please request a sample from us to assess the exact colour and texture before specifying.

Colorcoat[®] SDP 50 is an aesthetic, durable and resilient prefinished steel with long guaranteed life expectancy. It is the perfect material for profiles and sandwich panels for walls and roofs of premium architectural projects.

- 50µm coating for improved scratch and abrasion resistance combined with excellent corrosion protection.
- Colorcoat SDP 50 complies with the recommendation of the IFBS, to specify a coating thickness of at least 45μ for roofs used for services or solar installations
- Up to 25 years performance guarantee from Tata Steel. No registration required. The guarantee also applies when solar panels are installed
- Ruv4 and RC5+
- Low carbon footprint, a third party verified EPD is available
- BES 6001 certified. Fully REACH compliant. Available with Zeremis® Carbon Light

TATA STEEL



Wide range of colours

Colorcoat SDP 50 is available in a variety of standard roof and wall colours, including a number of metallic colours with a sparkling effect. The metallic colour range includes a copper green metallic and a silver white metallic.

Non-standard colours are also available upon request. Production hand samples are available for the best assessment of texture, colour and effect. To ensure consistency of colour on a single surface, it is recommended to use material from the same production batch.

In addition, for metallic colours, the directionality of the surfaces should be consistent during construction.

Tata Steel Performance Guarantee

- Up to 25 years guarantee
- Full coverage during entire period
- Guarantee also applies if solar modules are installed
- The guarantee starts automatically. No further action required
- Full coverage without any registration within Europe

The actual guarantee period and conditions are stated on the guarantee document.

Typical Properties

Colorcoat® SDP 50		Test norm
Nominal organic coating thickness	50 μm	EN 13523 - 1
Gloss level (60°)	20 – 40%	EN 13523 - 2
Flexibility:	1T @	EN 13523 - 7
Minimal bending radius	16°C	
Adhesion	≤ 1T	EN 13523 - 7
Corrosion resistance		
Salt spray test	1000 h	EN 13523 - 8
Condensation test	1500 h	EN 13523 - 26
Corrosion resistance class	RC5+	EN 10169
UV resistance	Ruv4	EN 10169
Reaction to fire, Class*	A1	EN 13501 - 1

^{*} Fire rating depends on thickness. Double sided has not been tested and classification may not be applicable. Please contact Tata Steel for more information.

Sales Contact Details

Tata Steel Nederland

Trademarks of Tata Steel

Wenckebachstaat 1
1951 JZ Velsen-Noord
The Netherlands
E: Connect.Colors@tatasteeleurope.com
www.tatasteelnederland.com

Tata Steel Maubeuge SAS

22, Av. Jean de Beco
59720 Louvroil
France
E: Connect.Colors@tatasteeleurope.com

www.tatasteelnederland.com

Colorcoat®, MyriaPlus®, MagiZinc® and Zeremis® are trademarks of Tata Steel. While care has been taken to ensure that the information contained in this publication is accurate, neither Tata Steel, nor its subsidiaries, accept responsibility or liability for errors or for information which is found to be misleading. Before using products or services supplied or manufactured by Tata Steel and its subsidiaries, customers should satisfy themselves as to their suitability.

Tata Steel IJmuiden BV is registered in The Netherlands under number 34040331 at Wenckebachstaat 1, 1951 JZ Velsen-Noord, The Netherlands.

Tata Steel Maubeuge SAS is registered in France under number 445 720 295 RCS Valenciennes, at 22, Av. Jean de Beco, 59720 Louvroil, France.